

WINDOW FILM PERFORMANCE DATA

Automotive: North America

% Visible Light Transmission % Total Solar Energy Rejection % IR Energy Rejection (IRER)*
 % Selective IR Rejection (SIRR)** % Ultraviolet Protection (wavelengths 300-380nm) % Glare Reduction*** % Visible Light Reflection

| CTX® Series (Ceramic Window Tint) | For excellent heat rejection without blocking electronic signal transmission | | | | | | |
|--|---|----|----|----|-----|----|---|
| CTX 05 CH SR HPR (Charcoal) | 5 | 58 | 50 | 72 | >99 | 94 | 5 |
| CTX 15 CH SR HPR (Charcoal) | 20 | 53 | 49 | 69 | >99 | 78 | 5 |
| CTX 25 CH SR HPR (Charcoal) ‡ | 28 | 50 | 47 | 66 | >99 | 69 | 5 |
| CTX 30 CH SR HPR (Charcoal) | 34 | 49 | 48 | 68 | >99 | 62 | 6 |
| CTX 35 CH SR HPR (Charcoal) | 37 | 48 | 48 | 69 | >99 | 58 | 6 |
| CTX 40 CH SR HPR (Charcoal) | 44 | 47 | 49 | 69 | >99 | 50 | 6 |
| CTX 50 CH SR HPR (Charcoal) | 55 | 43 | 48 | 68 | >99 | 37 | 7 |
| IRX™ Series (Infrared-Rejecting Ceramic Window Tint) | For our best heat rejection, advanced nanoceramic IR-blocking technology, and no sacrifices | | | | | | |
| IRX 05 CH SR HPR (Charcoal) ‡ | 6 | 62 | 60 | 86 | >99 | 94 | 5 |
| IRX 15 CH SR HPR (Charcoal) ‡ | 20 | 59 | 61 | 88 | >99 | 78 | 5 |
| IRX 25 CH SR HPR (Charcoal) ‡ | 26 | 57 | 59 | 85 | >99 | 70 | 5 |
| IRX 30 CH SR HPR (Charcoal) ‡ | 33 | 56 | 60 | 87 | >99 | 63 | 5 |
| IRX 35 CH SR HPR (Charcoal) ‡ | 39 | 54 | 60 | 87 | >99 | 56 | 6 |
| IRX 40 CH SR HPR (Charcoal) ‡ | 42 | 53 | 60 | 87 | >99 | 53 | 6 |
| IRX 50 CH SR HPR (Charcoal) ‡ | 54 | 50 | 60 | 87 | >99 | 39 | 7 |
| AIR Series (Clear Window Film) | For virtually invisible, ceramic protection against heat and harmful UV rays | | | | | | |
| AIR 80 BL SR HPR (Clear) | 77 | 43 | 60 | 86 | >99 | 13 | 9 |
| AIR 90 CL SR HPR (Clear) | 84 | 30 | 40 | 57 | >99 | 5 | 9 |

LLumar.com